

AUSTFIL EXCEL



WCD 7020

New Enhanced Formula for Consistently Great Results!

SUMMARY

- Rutile type flux-cored wire designed for all positional welding
- Formulated for 100% CO₂ and 75-80% Ar + 25-20% CO₂ shielding gases
- Excellent operator appeal and usability with stable arc, low spatter, smooth bead appearance and easy slag removal

CLASSIFICATION

- AS/NZS ISO 17632-B: T493T1-1 M A-U-H10, T493T1-1 C A-U-H5, T493T12-1 M A-U-H10, T493T12-1 C A-U-H5
- AWS A5.20: E71T-1M, E71T-1C
- E71T-9M, E71T-9C

DESCRIPTION AND APPLICATION

An all positional rutile micro alloyed type flux-cored welding wire specifically formulated for optimum performance using both CO₂ and Ar/CO₂ shielding gas mixtures.

The exceptionally smooth arc performance produces a superb weld for single or multipass welding with low spatter losses in all positions and applications (except vertical down). Austfil Excel is recommended for the welding of mild, carbon and carbon-manganese steels where good impact properties are required.

This high deposition flux-cored wire has been specially formulated to operate in a wider, more forgiving parameter range. It is suitable for general & heavy fabrication, structural steel fabrication, truck bodies, shipbuilding, earth moving equipment, storage tanks & bridge construction.

OPERATIONAL DATA

Wire size (MM)	Welding Current Range (A)	Arc Voltage Range *(V)
1.2	160 - 300	22 - 30
1.6	180 - 400	23 - 35

Recommended electrical stick out is 15-25mm.

Welding Current DC +

*Voltage is determined by arc current and wire arc length. Welding currents and voltage shown are operational guides only

SHIPPING APPROVAL

LR 100% CO₂ 3YS H5, 80/20 3YS H10 (Pending)

TYPICAL ALL WELD METAL CHEMICAL ANALYSIS

100% CO₂

C	Mn	Si	S	P	Ni
0.04	1.35	0.45	0.01	0.01	0.01

75%Ar+25%CO₂

C	Mn	Si	S	P	Ni
0.04	1.45	0.50	0.01	0.01	0.01

TYPICAL ALL WELD METAL MECHANICAL ANALYSIS

Gas Type	Ar+25% CO ₂	100% CO ₂
Yield Strength	530 MPa	580 MPa
Tensile Strength	610 MPa	550 MPa
Elongation	30.5%	32.8%
CVN Impact Values	80J @ -30°C	65J @ -30°C

PACKAGING DATA

Wire size (MM)	Pack size and type	Pallet size (KG)	Part No.
1.2	15kg spool	1080	AE71CM12
1.6	15kg spool	1080	AE71CM16



WCD 7020

OPERATIONAL DATA

Wire size (MM)	Weld position	Amps	Volts	Wire feed speed (M/MIN)	Depositor rate (KG/HR)	Contact tip to work distance (MM)
1.2	All Positions	160	24	6.6	2.54	16
		185	25	7.9	3.12	16
		200	26	7.7	3.48	16
		240	27	9.7	4.40	19
	Flat & Horizontal	280	32	12.7	5.70	19
		320	34	15.0	7.14	19
1.6	All Positions	180	24	4.1	2.11	25
		245	25	4.8	3.0	25
		275	26	5.7	3.5	25
	Flat & Horizontal	300	30	6.0	4.56	25
		360	31	8.4	6.18	25
		420	33	10.9	7.91	25

- Maintaining a proper welding procedure - including pre-heat and interpass temperatures - may be critical depending on the type and thickness of steel being welded.
- See above: This information was determined by welding using 100% CO₂ shielding gas with a flow rate between 17/24 l/min, When using 75% Ar/25% CO₂ shielding gas, reduce voltage by 1 volt.
- All positions include: Flat, Horizontal, Vertical Up, and Overhead.

The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and Welding Industries of Australia expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with the AWS A5.20 specification. Other tests and procedures may produce different results. No data is to be construed as a recommendation for any welding condition or technique by Welding Industries of Australia. Issue CA - February 2021